

EC13 300 Z20 TD37C H8

ECK 16 1/0 0.5Z TD37C H8



Single yarn

Provisional
Product
Specification

Technical characteristics

Control method		Nominal value	Lot tolerances		Individual tolerances		CV %	Quality control procedure
			Min	Max	Min	Max		
Linear density	tex	300,00	295,50	304,50	285,00	315,00	1,5	ISO 1889
	yds/lb	1.654	1.679	1.629	1.741	1.575		
Loss on ignition	%	0,50	0,45	0,55	0,40	0,60	7,0	ISO 1887
Moisture content	%	-	-	0,150	-	0,300	-	ISO 3344
Breaking force	N	190	162	-	143	-	-	ISO 3341
	lbf	42,71	36,31	-	32,04	-		
Twist	t/m	20	17,00	23,00	15,00	25,00	10,0	ISO 1890
	tpi	0,51	0,43	0,58	0,38	0,64		

Package information – Bobbin H8

		Nominal length	Lot		Individual value		Nominal weight		Percentage delivery
			Min	Max	Min	Max			
Metered splice free	m	27.000	27.135	27.675	27.000	27.810	kg	8,26	80
	yds	29.528	29.675	30.266	29.528	30.413	lbs	18,22	
Non metered		-					Min. kg	2,20	20
							Min. lbs	4,85	

Conditions of storage for the Vetrotex E-Glass products:

The material should be stored in its original packaging in dry conditions away from direct sunlight.

Storage temperatures of 10 to 35 °C and a relative humidity of 40 to 70% are recommended.

We recommend that the material be used within 24 months after the delivery date.

Before processing, the material should be conditioned, i.e. exposed unpacked at the ambient work shop temperature for at least 24 hours.

Bobbin disc:



Edition:
23.09.15

Saint-Gobain Vetrotex
Krefelder Strasse 195
52070 Aachen - Germany
www.vetrotextextiles.com

Information:

Europe:

Phone: +49 241 40020-0

E-mail: vetrotex.europe@saint-gobain.com

America/Asia/Australia:

Phone: +1 704 895 5906

E-mail: vetrotex.america@saint-gobain.com