



WOVEN FABRIC

Technical Data Sheet

Carbon Fabric

Product Code: **ST-200 P**

CHARACTERISTICS	Nominal	UM	Tolerance	Normative
Mass per unit area	200	g/m ²	± 5%	ISO 4605
Weave	Plain			ISO 2113
Width	1000	mm	± 2,5%	ISO 22198
Thickness	0,19	mm	± 2,5%	ISO 5084(**)
Other informations	Loomstate			

Nominal Construction	WARP		WEFT	
Fiber Description	HS Carbon Fiber T700SC 50C - 12K		HS Carbon Fiber T700SC 50C - 12K	
Fiber Producer	TORAY		TORAY	
Thread Count	1,3 ends/cm	ISO 4602	1,3 ends/cm	ISO 4602
Weight Distribution	100 g/m ²	50%	100 g/m ²	50%
Selvadges	Weaving style	LENO	Type of Fiber	HM polyester 22 tex

Mechanical Properties of Fiber	Strength (nominal)	Modulus (nominal)
T700SC 50C - 12K (TORAY)	4900 MPa	230 GPa

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

Date of Issue

19/03/2018

G.Angeloni srl

via Abate Tommaso , 72/A5 - 30020
Quarto d'Altino (VE) - ITALY

Web Site: www.g-angeloni.it
E-Mail : info@g-angeloni.com

Tel. +39 0422 780580
Fax +39 0422 782782