

CHARACTERISTICS	
Mass per unit area	gr/sqm.
Weave	
Standard Width	mm.
Laminate thickness	mm.
Other informations	

Nominal	Tolerance	Normative
200	± 5%	ISO 4605
2x2 Twill		ISO 2113
1000	± 2,5%	
0,25	± 15%	ISO 5084
Loomstate		

Nominal Construction	
Fibre description	
Thread Count	ends/cm.
Weight distribution	gr/sqm.
	%

WARP		WEFT	
Black HT Polyester fiber		Black HT Polyester fiber	
167 tex		167 tex	
6,00	ISO 4602	6,00	ISO 4602
Polyester fiber	100	Polyester fiber	100
	50%		50%

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.