

Technical Datasheet - METYX Composite Reinforcements

PRODUCT CODE	5200.003.188
PRODUCT NAME	XL800E10G-0/45/45 TRIAXIAL ECR GLASS FABRIC-127CM
PRODUCT DESCRIPTION	.
CUSTOMER CODE	.
CUSTOMER ID	.

REINFORCEMENT CONSTRUCTION			
LAYER	FIBER TYPE	AREA WEIGHT	
1	0°	1200 Tex - ECR Glass	378 gr / m2
2	+45°	300 Tex - ECR Glass	217 gr / m2
3	90°	200 Tex	12 gr / m2
4	-45°	300 Tex - ECR Glass	217 gr / m2
5	Stitch	76 Dtex	10 gr / m2
6			
7			

* Checked via own test based on ISO 3374.

TOTAL* **834 gr / m2** (± %3)

OTHER PROPERTIES		ROLL INFO	
Stitch Gauge	10 stitches/inch	Roll Width	127 cm
Stitch Type	Tricot	Roll Weight	68 kg
Stitch Length	3 mm	Roll Length	65 m
Pilot Yarn / Position	Yellow-Red	Core Diameter	76 mm

Resin Compatibility	Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins	Max.%0,70 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)

Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.
Storage	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.

Certification	DNV	Lloyd's Register
Metyx products are produced by Telateks A.S. company who is run by ISO 9001:2008 QA System.	TYPE Approved	-

Note: The above specifications reflect the product data on release date but are subject to change without prior notice.

Address:
Orhanli Beldesi 34956
Tuzla Istanbul – TURKIYE



Phone : +90-216-394-32-60
Fax : +90-216-394-32-58
Web : www.metyx.com