TECHNICAL DATA SHEET

GG 400 NT 127 100 12K C12MM

CHOPPED FIBRE REINFORCEMENT

Fiber aeral weight (FAW) [g/m²]	300
Width [mm]	1270
Filament count	12K
Filament yield [tex]	800
Chopped fibre length [mm]	12
Support	Nonwoven carbon
Support FAW [g/m²]	100

FIBER SPECIFICATIONS

Grade	HS
Precursor	PAN
Filament diameter [µm]	7
Tensile strength [MPa]	4900
Tensile modulus [GPa]	230
Elongation at break [%]	2,1
Density [g/cm³]	1,79

NOTE: All technical information contained in this document are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any contract. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. The information contained herein is under constant review and liable to be modified. All products are sold subject to Microtex Composites Srl terms and conditions of sale. Copyright 2020 - Microtex Composites Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.

Distributor:
Castrocomposites
Pol. Ind. A Granxa, 3ª Paralela
C/Cíes 190, 36400 O Porriño – ESPAÑA
Tel. +34 986 342 955
shop@castrocomposites.com
www.castrocomposites.com

Microtex Composites S.r.l.
Via Toscana, 59 - 59100 Prato (Italy)
Tel. +39 0574 627298
info@microtexcomposites.com
www.microtexcomposites.com

Quality system certified
ISO 9001:2015
by TUV Italia s.r.l.
cert. no. 50 100 12429

Quality system certified
IATF 16949:16
by TUV SUD Management Service GmbH
cert. no. 0365935