

Crystic® Gelcoat 65PA

Isophthalic Gelcoat for Brush Application

Product Description

Crystic® Gelcoat 65PA is a high performance isophthalic gelcoat. It is pre-accelerated and formulated for brush application. The information contained in this technical data sheet applies to all colours.

Crystic® Gelcoat 65PA is recommended for use in all markets including marine, land transport and building applications. It is also suitable for general moulding requirements. Crystic® Gelcoat 65PA is approved by Lloyd's Register of Shipping.

Features and Benefits

| Features | Benefits |
|------------------------|---|
| Isophthalic base resin | Excellent water / blistering resistance |
| High elongation | Good impact resistance |
| Easy to apply | Excellent surface finish |

Brush Application

| Do | Don't |
|--|--|
| Ensure the gelcoat has attained workshop temperature of 15°C - 25°C before use. | Stir the gelcoat with high shear mixers as this will temporarily break down the thixotropy leading to drainage. |
| Add 2% Butanox® M-50 or equivalent catalyst. | Exceed a wet film thickness of 800 microns as thick films encourage air retention. |
| Gently stir the gelcoat by hand or low shear stirrer. | Apply excessive thickness in corner areas as this can cause pre-release. |
| Use long brush strokes and even pressure to apply the gelcoat in an even film across the mould surface | Apply backing laminate before the gelcoat has reached an appropriate degree of cure. |
| Brush through the gelcoat until the recommended wet film thickness of 600-800 microns is reached. | Catalyse more gelcoat than can be applied before it starts to gel as this will lead to wastage and possible exothermic reaction. |
| Apply the first layer of laminate within 24 hours of the gelcoat. | Allow vapour to be retained in deep mould sections as this can cause slow curing. |

Additives and Variants

The information contained in this technical data sheet applies to all pigmented versions.

A topcoat version of this material is available called 65PAX. The topcoat can be formulated by addition of 2% Crystic® Solution MW into the gelcoat. A non-accelerated version, Crystic® Gelcoat 65, can also be supplied.

Incorporation of additional material may affect the working, weathering or cured properties of the gelcoat. Please check with Scott Bader's Technical Service department before using the gelcoat outside of specified parameters.

Post-Curing

Satisfactory laminates for many applications can be made with Crystic® Gelcoat 65PA by curing at workshop temperature (15°C - 25°C). However, for optimum properties, laminates must be post-cured before being put into service. The moulding should be allowed to cure for 24 hours at workshop temperature, and then oven-cured for 16 hours at 40°C.

Recommended Testing

It is recommended that customers test all pigmented gelcoats before use under their own conditions of application to ensure that the product meets requirements.

Typical Properties – Uncured

| Property | Typical Value |
|-------------------------------------|---------------|
| Viscosity, 25°C 0.6s ⁻¹ | 400 poise |
| Viscosity, 25°C 4500s ⁻¹ | 15 poise |
| Specific Gravity at 25°C | 1.1 |
| Styrene Content | 34% |

Typical Properties – Cured

| Property | Test Method | Typical Value |
|---|-----------------------|---------------|
| Barcol Hardness (Model GYZJ 934-1)* | EN59 | 42 |
| Water Absorption 24 hrs at 23°C* | BS EN ISO 62 part 6.2 | 18 mg |
| Heat Deflection Temperature [†] (1.8MPa) | BS EN ISO 75-2 (1996) | 75°C |
| Elongation at Break* | BS EN ISO 527-2 | 3% |
| Tensile Strength* | BS EN ISO 527-2 | 75 MPa |
| Tensile Modulus* | BS EN ISO 527-2 | 3500 MPa |
| Flexural Strength* | BS EN ISO 178 | 126 MPa |
| Flexural Modulus* | BS EN ISO 178 | 4300 MPa |

* Curing Schedule - 24hrs at 20°C, 3hrs at 80°C.

† Curing Schedule - 24hrs at 20°C, 5hrs at 80°C, 3hrs at 120°C.

Gel time & Backup time

Catalyst level and temperature will influence the gel time. The product only requires the addition of catalyst to start curing. We recommend the use of a 50% MEKP (type Butanox[®] M-50) which should be added at 2% in the gelcoat.

| Temperature | Gel time (2% Butanox [®] M-50)** | Backup time (2% Butanox [®] M-50)** |
|-------------|---|--|
| 15°C | 19 minutes | 90 minutes |
| 20°C | 12 minutes | 45 minutes |
| 25°C | 9 minutes | 30 minutes |
| 30°C | 6 minutes | 25 minutes |

**Measured under laboratory conditions. Information should be used as a guide only.

Packaging and Storage

Crystic[®] Gelcoat 65PA is supplied in 25kg and 225kg containers.

Crystic[®] Gelcoat 65PA should be stored in its original container, under cover, and out of direct sunlight. These must be kept closed and airtight. It is recommended that the storage temperature should be less than 25°C and the product should not be frozen. Storing the product outside of these conditions may affect the properties of the product and reduce its shelf life. Ideally, containers should be opened only immediately prior to use. Material should be used within 5 months from date of production.

Health and Safety

Read and understand separate Material Safety Data Sheet before using this product. Unsaturated polyester products release heat when they cure in bulk.

Eng - 65PA - June 2017

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com