

# Aramid Tape

## WOVEN TAPE DATA SHEET

### TKB 170

CHARACTERISTICS		Nominal	Tolerance	Normative
Mass per unit area	g/sqm	<b>170</b>	± 5%	ISO 4605
Weave		<b>Plain</b>		ISO 2113
Standard Width	mm	from 10 mm. to 200 mm.	± 2,5%	
Laminate thickness	mm	<b>0,19</b>	± 2,5%	(**)
Other informations				

  

Nominal Construction		WARP	WEFT
Fibre description		aramid Twaron 2200 - 1210 dtex	aramid Twaron 2200 - 1210 dtex
Thread Count	ends/cm	<b>7,0</b> ISO 4602	<b>3,5 x 2</b> ISO 4602
Weight distribution	g/sqm	aramid Twaron <b>85</b> 50%	aramid Twaron <b>85</b> 50%
	%		
	g/sqm		
	%		

(\*\*) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.