



TECHNICAL DATA SHEET

WOVEN FABRIC GK165P



CHARACTERISTICS	
Mass per unit area	gr/sqm.
Weave	
Standard Width	mm.
Laminate thickness	mm.
Other informations	

Nominal	Tolerance	Normative
168	± 5%	ISO 4605
Plain		ISO 2113
1000/1200	± 2,5%	
0,17	± 15%	ISO 5084
Loomstate		

Nominal Construction	
Fibre description	
Thread Count	ends/cm.
Weight Rate	%
Weight distribution	gr/sqm.
	%
	gr/sqm.
	%

WARP		WEFT	
3K Carbon fibre 200 tex		3K Carbon fibre 200 tex	
HM Aramid 1610 dtex		HM Aramid 1610 dtex	
4,60 ISO 4602 Last updated : 2023-06-06 52%		4,60 ISO 4602 48%	
3K Carbon fibre	62	3K Carbon fibre	31
	71%		38%
HM Aramid	25	HM Aramid	50
	29%		62%

Note : Technical information furnished is based on laboratory findings and believed to be correct.
No warranties of any kind are made except that the materials supplied are of standard quality.
All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.