

EC13 300 Z20 TD37C H8

ECK 16 1/0 0.5Z TD37C H8



Single yarn

Product Specification

Technical characteristics

Control method		Nominal value	Lot tolerances		Individual tolerances		CV %	Quality control procedure
			Min	Max	Min	Max		
Linear density	tex	300,00	295,50	304,50	285,00	315,00	1,5	ISO 1889
	yds/lb	1.654	1.679	1.629	1.741	1.575		
Loss on ignition	%	0,50	0,45	0,55	0,40	0,60	7,0	ISO 1887
Moisture content	%	-	-	0,150	-	0,300	-	ISO 3344
Breaking force	N	180	135,0	-	117,0	-	-	ISO 3341
	lbf	40,47	30,35	-	26,30	-		
Twist	t/m	20	17,00	23,00	15,00	25,00	10,0	ISO 1890
	tpi	0,51	0,43	0,58	0,38	0,64		

Package information – Bobbin H8

		Nominal length	Lot		Individual value		Nominal weight		Percentage delivery
			Min	Max	Min	Max			
Metered splice free	m	27.000	27.135	27.675	27.000	27.810	kg	8,26	80
	yds	29.528	29.675	30.266	29.528	30.413	lbs	18,22	
Non metered		-					Min. kg	2,20	20
							Min. lbs	4,85	

Conditions of storage for Vetrotex E-Glass products:

The material should be stored in its original packaging in dry conditions away from direct sunbeam.

Storage temperatures of between 10 and 35 °C (50 and 95 °F) and a relative humidity of between 40 and 70% are recommended.

Though there are no known storage limitations under proper conditions, we recommend to use the material within 6 months after delivery date, or within 24 months after date of manufacture. Retesting is advised after 2 years from initial manufacture date to insure optimum performance.

Before processing, the material should be conditioned by exposing it unpacked to the processing climate for at least 24 hours.

Bobbin disc:



Edition:

18.10.17

Saint-Gobain Vetrotex

Krefelder Strasse 195
52070 Aachen - Germany
www.vetrotextextiles.com

Information:

Europe:

Phone: +49 241 40020-0

E-mail: vetrotex.europe@saint-gobain.com

America/Asia/Australia:

Phone: +1 704 895 5906

E-mail: vetrotex.america@saint-gobain.com